

# POLYHEED<sup>®</sup> 916N

Mid range water reducer with superior pumping and finishing

## DESCRIPTION

**POLYHEED 916N** is a multi component, non-chloride, mid range water reducing admixture designed to improve the performance of concrete both in the plastic and hardened states. **POLYHEED 916N** is a versatile admixture able to produce mid range slumps without retardation. Its formulation contains materials able to improve the concrete's workability and finishability. **POLYHEED 916N** meets and exceeds the requirements of AS1478 Type MWR.

## RECOMMENDED FOR

- all types of concrete where a non-chloride water reducing admixture is required, especially in the mid range slump band (100-150mm)
- improving the performance of pumped concrete, shotcrete and conventionally placed concrete
- improving the performance of plain, reinforced, precast, light weight or standard weight concrete
- use in white or coloured concrete
- use in architectural concrete, especially where off-form and/or surface finish is critical
- use in concrete containing harsh aggregates and/or manufactured sands

## FEATURES AND BENEFITS

**POLYHEED 916N** mid range water reducer aids in the production of concrete with these qualities.

In the plastic state:

- **normal setting characteristics throughout the recommended dose range**
- **reduced segregation, particularly in lean mixes and mid slump concrete**
- **improved workability**
- **improved pumpability**
- **reduced water content for a given workability**
- **enhanced finishability, especially for concrete with manufactured or harsh aggregates**

In the hardened concrete:

- **no added chlorides, conforms to the most stringent chloride ion limits including AS3600 concrete structures code, will not initiate or promote the corrosion of reinforcing steel**
- **increased strength – compressive, flexural and bond (concrete to steel)**
- **superior finished appearance**
- **increased density and durability**
- **reduced permeability – improved watertightness**
- **reduced cracking**

## CAUTION

**POLYHEED 916N HAS A SYNERGISTIC EFFECT WITH AIR ENTRAINING AGENTS (AEA) WHICH MAY PRODUCE UP TO FOUR TIMES THE VOLUME OF ENTRAINED AIR.**

## QUANTITY TO USE

**POLYHEED 916N** is a versatile admixture with a dose rate of 300 to 1200 mls per 100kg of cementitious material. An increase in dose rate results in an increase in water reduction.

The improved pumpability and finishability aspects of **POLYHEED 916N** are enhanced with increasing dose rate. The correct dosage rate in each instance should be determined by correctly conducted trials under the supervision of a BASF Technical Sales Representative.

## DISPENSING

**POLYHEED 916N** can be added at the batch plant or on site. When adding at batch plant, delay addition until cement has been thoroughly wetted out and at least 75% of water added. When introduced on site, mix for a further 4 minutes after addition.

## COMPATABILITY

**POLYHEED 916N** is not compatible with admixtures containing sulfonated naphthalene formaldehyde condensates (BNS).

**POLYHEED 916N** can be used with other BASF admixtures to achieve cost effective customised performance. However, those admixtures should be dispensed separately and added separately to ensure complete distribution throughout the mix. **POLYHEED 916N** should not be used in conjunction with other admixtures unless specific test information is available.

## PACKAGING

**POLYHEED 916N** is supplied in 20 litre pails, 205 litre drums, 1000 litre pallecons and bulk delivery.

## PRECAUTIONS

If **POLYHEED 916N** has frozen, thaw at 2°C or above and completely reconstitute by mild mechanical agitation. Do not use pressurised air for agitation.

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the **BASF Material Safety Data Sheet (MSDS)** from our office or our website.



The Chemical Company

# POLYHEED<sup>®</sup> 916N

---

APheed916N/4/0611

---

**STATEMENT OF  
RESPONSIBILITY**

The technical information and application advice given in this **BASF** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. **BASF data sheets are updated on a regular basis and it is the user's responsibility to obtain the most recent issue.**

---

**NOTE**

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF**, are responsible for carrying out procedures appropriate to a specific application.

---

**BASF Australia Ltd** A.B.N. 62008437867

**Sydney-Head Office:** 11 Stanton Road Seven Hills, NSW 2147 Australia Ph. (02) 8811 4200

**Newcastle:** (02) 4961 3819 **Brisbane:** (07) 3633 9900 **Townsville:** (07) 4774 7344 **Melbourne:** (03) 9549 0300

**Adelaide:** (08) 8139 7500 **Perth:** (08) 9366 2600 **Kalgoorlie:** 0417 772 355

**BASF New Zealand Ltd** **Office:** 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233

**BASF Websites:** [www.basf-cc.com.au](http://www.basf-cc.com.au) [www.basf-cc.co.nz](http://www.basf-cc.co.nz) [www.meyco.basf.com](http://www.meyco.basf.com)

---