

POZZOLITH[®] 122Ri

Polymer admixture for improving concrete

DESCRIPTION

POZZOLITH 122Ri is a ready-to-use liquid admixture for making better, more uniform and more predictably high quality concrete. It retards the setting time to facilitate placing and finishing. Concrete meeting architectural, structural and construction requirements is obtained more dependably and economically with **POZZOLITH 122Ri**. **POZZOLITH 122Ri** meets and exceeds AS1478 requirements for Type Re admixtures.

RECOMMENDED FOR

POZZOLITH 122Ri admixture is recommended for use in all types of concrete where retardation of set is required or desired.

POZZOLITH 122Ri admixture improves pumped concrete, shotcrete (wet mix) and conventionally placed concrete; it improves plain, reinforced, precast, prestressed, lightweight or standard weight concrete. It can be used in white or coloured concrete. **POZZOLITH 122Ri** is the ideal admixture to be used for stencilled and/or stamped concrete. **POZZOLITH 122Ri** can be used with air-entraining agents approved under AS 1478 Specifications when air-entrained concrete is specified or desired.

BASF approved air-entraining admixture **MICRO-AIR** is recommended for use with **POZZOLITH 122Ri** admixture when air-entrained concrete is specified or desired.

When used in conjunction with another admixture each admixture must be dispensed separately into the mix.

FEATURES AND BENEFITS

POZZOLITH 122Ri admixture aids in the production of concrete with these special qualities.

- Mild to extended retardation - depending on dosage
- Greater pumpability
- Superior finishing characteristics for slabwork and off-form surfaces
- Increased strength - compressive, flexural and bond of concrete to steel
- Greater economy in a mix designed for a given strength, slump and air content
- Easier placement - economy in placement
- Greater durability
- Slipformed concrete

QUANTITY TO USE

POZZOLITH 122Ri is used at the rate of 200±100ml per 100kg cement. Similar dose rates may be used with blended cements.

Whilst **POZZOLITH 122Ri** effects setting time, it has little or no effect on water reduction.

RATE OF HARDENING

The temperature of the concrete mix and the ambient temperature (forms, earth, reinforcement, air, etc.) affect the rate of hardening of the concrete. At higher temperatures concrete hardens more rapidly and may impose problems with placing and finishing of concrete. By varying the dosage of **POZZOLITH 122Ri**, concrete with a more desirable rate of hardening characteristic can be obtained.

Since setting time is also influenced by the chemical and physical composition of the basic ingredients of the concrete, trial mixes should be made with the job materials approximating job conditions to determine the dosage required for a given degree of retardation.

COMPRESSIVE STRENGTH

In comparison to plain concrete, a mix containing **POZZOLITH 122Ri** develops higher early and ultimate strengths, exceeding the strength requirements of AS 1478.

PACKAGING

POZZOLITH 122Ri is supplied in 205 litre sealed drums, 1000 litre pallecons and bulk delivery.

For additional information on **POZZOLITH 122Ri** and its use in developing a concrete mix with special performance characteristics, contact your local BASF Technical Sales Representative.

PRECAUTION

If **POZZOLITH 122Ri** has frozen, thaw at 2°C or above and completely reconstitute by mild mechanical agitation. Do not use pressurised air for agitation.

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF **Material Safety Data Sheet (MSDS)** from our office or our website.



The Chemical Company

POZZOLITH[®] 122Ri

AP122Ri/5/0711

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF**, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd

A.B.N. 62008437867

Head Office: 11 Stanton Road Seven Hills, NSW 2147

Ph. (02) 8811 4200

Newcastle	(02) 4961 3819
Canberra	(02) 6280 6010
Brisbane	(07) 3633 9900
Townsville	(07) 4774 7344
Melbourne	(03) 9549 0300

Adelaide	(08) 8139 7500
Perth	(08) 9366 2600
Darwin	(08) 8984 3269
Kalgoorlie	0417 772 355

BASF New Zealand Ltd BASF WEB SITES

Head Office: 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233
www.basf-cc.com.au www.basf-cc.co.nz www.meyco.basf.com
