

# POZZOLITH<sup>®</sup> 370

Non-chloride water-reducing admixture

## DESCRIPTION

**POZZOLITH 370** is a ready to use liquid admixture formulated to improve the performance of concrete in both the plastic and hardened states. **POZZOLITH 370** is a non-retarding, water reducing, strength enhancing admixture which does not contain added chloride.

## RECOMMENDED FOR

- All types of concrete where a non-chloride water reducing admixture is required.
- Improving the performance of pumped concrete, shotcrete and conventionally placed concrete
- Improving the performance of plain, reinforced, precast, lightweight or standard weight concrete
- Concrete subject to chloride ion constraints such as in coastal environments
- Use in white or coloured concrete
- Use in architectural concrete
- Concrete placed on galvanised steel floor and roof systems which are left in place

## FEATURES AND BENEFITS

**POZZOLITH 370** admixture aids in the production of concrete with these special qualities:

In the plastic state:

- **Superior finishing characteristics for slab work and off-form surfaces**
- **Normal setting characteristics under cool conditions allowing earlier finishing of slabs**
- **Reduced segregation particularly in lean mixes and high slump concrete**
- **Improved workability**
- **Improved pumpability**
- **Reduced water content for a given workability**

In the hardened concrete:

- **No added chlorides, conforms to the most stringent chloride ion limits including AS3600 concrete structures code, will not initiate or promote the corrosion of reinforcing steel**
- **Increased strength - compressive, flexural and bond (concrete to steel)**
- **Superior finished appearance**
- **Increased density and durability**
- **Reduced permeability - improved watertightness**
- **Reduced cracking**
- **Compatibility with air entraining agents**

## QUANTITY TO USE

**POZZOLITH 370** admixture is normally used at a dose rate of 300mL per 100kg of cementitious material depending on the composition of the basic ingredients of the concrete and ambient conditions. **POZZOLITH 370** can be used in summer at 400 to 500mL per 100kg of cementitious material resulting in increased water reduction. The correct dosage rate in each instance should be determined by correctly conducted trials under the supervision of a BASF Construction Chemicals Technical Sales Representative.

## COMPATABILITY

**POZZOLITH 370** can be used with air entraining agents and other BASF admixtures to achieve cost effective customised performance. However, all admixtures should be dispensed separately and added separately to initial batching water to ensure complete distribution throughout the mix. **POZZOLITH 370** can also be used in mix designs including flyash, slag and silica fume. **POZZOLITH 370** should not be used in conjunction with other admixtures unless specific test information is available.

## PACKAGING

**POZZOLITH 370** is supplied in 205 litre sealed drums and bulk delivery.

## PRECAUTIONS

If **POZZOLITH 370** has frozen, thaw at 2°C or above and completely reconstitute by mild mechanical agitation. Do not use pressurised air for agitation.

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF **Material Safety Data Sheet (MSDS)** from our office or our website.



The Chemical Company

# POZZOLITH<sup>®</sup> 370

---

AP370/7/0711

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF**, are responsible for carrying out procedures appropriate to a specific application.

<b>BASF Australia Ltd</b> A.B.N. 62008437867 Head Office: 11 Stanton Road Seven Hills, NSW 2147 Ph. (02) 8811 4200	Newcastle (02) 4961 3819 Canberra (02) 6280 6010 Brisbane (07) 3633 9900 Townsville (07) 4774 7344 Melbourne (03) 9549 0300	Adelaide (08) 8139 7500 Perth (08) 9366 2600 Darwin (08) 8984 3269 Kalgoorlie 0417 772 355
---	---	---

<b>BASF New Zealand Ltd</b> <b>BASF WEB SITES</b>	Head Office: 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233 www.basf-cc.com.au      www.basf-cc.co.nz      www.meyco.basf.com
--	--