

MBRACE® LAMINATE

(GRADES 165/2500, 170/3100 & 210/3300)

The MBRACE® Laminate System is a Carbon Fibre Reinforced Polymer (CFRP) system for structural strengthening of concrete and timber structures. The system comprises of a heavy-duty MBRACE Laminate Adhesive which is used to bond the ready to use MBRACE Laminates.

DESCRIPTION

MBRACE Laminate is a ready to use pultruded, carbon fibre laminate, normally externally bonded to structures, to provide additional load bearing capacity. It provides a lightweight, high tensile strength material (higher than steel reinforcement used in the concrete industry) and is largely utilised for additional flexural reinforcement (ie plate bonding) of concrete and timber members, as part of the **MBRACE Laminate** system.

RECOMMENDED FOR

To add strength and reinforce structures with material that has a high tensile capacity, **MBRACE Laminate** enables the traditional technique of plating (with steel plates) to be replaced with extremely light materials, that are far easier to install, and to:

- increase the flexural capacity of beams and slabs
- increase the general load-bearing capacity (e.g. structural conversion following an increase in loading conditions)
- help reduce deflection of the overall structural element (increase in rigidity)
- help increase the fatigue strength (reduced maintenance)
- help to increase the crack resistance of a structure (increase in durability)

FEATURES AND BENEFITS

- Allows fast and easy installation, thereby reducing overall cost.
- Provide a durable, non-corroding solution.
- Low profile (thickness) does not impact on architectural aesthetics.
- Simple design enables the amount of reinforcement to be calculated in relation to the performance required or the flow of stress.
- A range of sizes and grades available to optimize design requirements.
- All laminates are supplied with a protective peel-ply to both faces, reducing preparation costs, whilst delivering better adhesion to the substrate and to any subsequent coatings.
- May be applied to grooves in the substrate for near surface mounting (NSM).

Note: Values given in the Performance Data table are mean values obtained from regular, quality assurance testing. Some variation may occur dependant on batch, size, and test method sensitivity. Allowance should be made for this in the design process.

The structural designer is advised to satisfy themselves, by prior testing if necessary, that the grade chosen will conform to the performance criteria for their specific design requirements.

PERFORMANCE DATA

MBRACE Laminate (Grade)	165/2500	170/3100	210/3300
Mean Tensile strength (MPa)	2500	3100	3300
Mean Tensile modulus E (GPa)	165	170	210
Laminate Width (mm)	50, 80, 100 typical (120, 150 on request) * Note: Other widths maybe manufactured to order		
Laminate Thickness (mm)	1.2 or 1.4 * Note: Other thicknesses maybe manufactured to order		
Ultimate Elongation (at break)	1.3%	1.6%	1.4%
Fibre content %	70	70	70
Density g/cm ³	1.6	1.6	1.6
Inter Laminar Shear Strength	80 MPa	80 MPa	80 MPa
Thermal Expansion m/m/°C	0.6 x10 ⁻⁶	0.6 x10 ⁻⁶	0.6 x10 ⁻⁶

APPLICATION

Preparation of Substrate

The surfaces of elements that are still in good condition or restored with a leveling material from the BASF range, should be sanded down and left clean and dry. With degraded structures, the whole damaged area should be removed by scarifying, hydro-demolition or similar, and then structural restoration carried out with mortar from the **EMACO** or **CONGRESIVE** range of products (eg **EMACO NANOCRETE R4** or **CONGRESIVE 1444**). Remove oils, grease, dust or any other loose material from the surface and leave dry.

Application

To ensure maximum adhesion, apply one coat of **MBRACE Primer** by roller or brush.



The Chemical Company

MBRACE® LAMINATE (GRADES 165/2500, 170/3100 & 210/3300)

If necessary, apply a coat of **MBRACE Laminate Adhesive or CONCRETSIVE 1444** using a putty knife, to fill any blow holes or imperfections to the concrete or timber surfaces.

Remove the protective peel-ply film from one surface of MBRACE Laminate to be adhered. If the type of Laminate being used does not have a peel-ply surface, then wipe clean the Laminate surface with a suitable solvent (**THINNER No1**, MEK or Acetone).

Apply one layer of **MBRACE Laminate Adhesive** 1 – 1.5 mm thick on both the surfaces (concrete and Laminate). Apply Adhesive on the Laminate so that it is a minimum of 1 mm thick at each side, and 2 mm thick at the centre by using an appropriately shaped spatula.

Apply **MBRACE Laminate** and using the correct hard roller, exert a constant pressure by moving the tool backward and forward, in the direction of the fibres, along the centre-line of the laminate. Expel any excess **MBRACE Laminate Adhesive** (and air) from under the Laminate, leaving a nominal 1-3 mm layer of adhesive.

Clean up the surfaces of the Laminate, taking care not to move the bonded material.

For detailed information about application, please obtain a copy of the BASF "Application Guide for MBRACE" from your local representative.

PACKAGING

Available in rolls, typically 100 m long. (Approx 30kg in weight, depending on size).

STORAGE

Store at ambient temperatures, out of direct sunlight, in cool, dry warehouse conditions.

SHELF LIFE

Up to 12 months if stored to manufacturer's instructions.

WATCHPOINTS – DESIGN AND INSTALLATION

Design and detailed specification should be carried out by appropriately qualified and competent person(s).

Professional consulting engineers and designers may make use of a special design programme for the MBRACE Laminate system. Please contact your local BASF Construction Chemicals office for further details.

Installation should only be carried out by trained and experienced specialist contractors. Site quality control (including tensile bond testing), should be the responsibility of an independent organisation appointed by the client or his representatives.

Surfaces exposed to U.V. rays should be protected within two days (maximum seven days) with a selected product from the **MASTERSEAL** range (eg **MASTERSEAL 160**), in order to ensure perfect bonding between the protective layer and CFRP. Remove the outer layer of peel-ply prior to application of protective coating.

Technical details of adhesives, primers and coatings can be found on the technical data sheets of the respective products.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Construction Chemicals **Material Safety Data Sheet (MSDS)** from our office or our website

SPECIFICATIONS

Professional consulting engineers and designers may also make use of standard specification details. Please make sure that you obtain a copy of the "MBRACE Laminate Specification" from your local office.

MBRACE Laminate is typically designated on drawings as per the example below:

"Apply six (6) no. lengths of **MBRACE Laminate 170/3100 – 100 x 1.4 mm**, positioned at 400 mm centres x 7000 mm long, as located on the drawings.

Typical installation is to be in accordance with manufacturer's recommendations."

AMBRACELamLMMM/7/1011

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF**, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd
A.B.N. 62008437867
Head Office: 11 Stanton Road Seven Hills, NSW 2147
Ph. (02) 8811 4200

Newcastle (02) 4961 3819
Canberra (02) 6280 6010
Brisbane (07) 3633 9900
Townsville (07) 4774 7344
Melbourne (03) 9549 0300

Adelaide (08) 8139 7500
Perth (08) 9366 2600
Darwin (08) 8984 3269
Kalgoorlie 0417 772 355

BASF New Zealand Ltd
BASF WEB SITES

Head Office: 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233
www.basf-cc.com.au www.basf-cc.co.nz www.meyco.basf.com