

MBRACE[®] PRIMER

Epoxy resin primer for MBRACE (Fibre Reinforced Polymer) Systems

DESCRIPTION

MBRACE Primer is the recommended primer to ensure maximum bond for **MBRACE Laminate Adhesive** and **MBRACE Saturant**.

MBRACE Primer is a two-part epoxy product with low viscosity and 100% solids content.

The **MBRACE Composite Strengthening System** is a family of lightweight FRP materials, externally bonded to the surface of structures. They comprise of either ready to use carbon laminate adhered directly to the surface or carbon, aramid or glass fibre sheets impregnated in situ, with a saturant resin system, on the surface. The systems provide very high tensile strength and are utilised for flexural and shear reinforcement and axial compression confinement of concrete, masonry and timber elements.

FEATURES AND BENEFITS

- **Ready-to-use (no need to add filler)**
- **Convenient pot-life**
- **High adhesive and bond strength**
- **Low viscosity, good for poor substrates**
- **Bonds to damp surfaces (saturated surface dry)**
- **High mechanical strength**
- **Solvent-free**

PERFORMANCE DATA

(Typical physical properties)

Bonding to concrete, pr EN 1542 (direct)	> 3.5 MPa (concrete failure)
Ultimate elongation, ASTM D638	3%
Tensile strength:	
• direct, ASTM D638	>12 MPa
• by flexing, ASTM D790	>24 MPa
Modulus of elasticity:	
• tensile, ASTM D638	>700 MPa
• flexural, ASTM D790	>580 MPa

SPECIFICATIONS

Composition	Two-part
Type of resin	Epoxy
Solids by volume	100%
Mixing ratio	by volume: 3 A; 1 B
Specific gravity	1.08 ± 0.024 kg/L
Colour	Transparent
Overall thickness/coverage	150 micron approximately 6-8m ² /L
Recommended layers	1
Pot life	7°C; 1 hour 23°C; 35 min 32°C; 25 min
Tack-free	7°C; 9 hours 23°C; 5 hours 32°C; 3 hours

SPECIFICATIONS continued

Over coating time with

- CONCRECIVE 1444/1446
- with MBRACE Resins

- | | |
|---------------------------------|-------------|
| a. recommended | While tacky |
| b. maximum (after sand seeding) | 48 hours |

Optimal storage

18-24°C

Tool cleaning

Thinner No.1

PACKAGING

Packaging (5lt kit)

A – 3.75 L

B – 1.25 L

APPLICATION DIRECTIONS (Brief Instructions)

- For detailed instructions, refer to the “MBRACE Application Guidelines for MBRACE S&P CFK Laminates or MBRACE FRP Fabric (Sheet)” documents.
- Application of external reinforcement may only take place if the substrate has an inherent tensile strength of at least 1.5 MPa for laminates and 1.0MPa for sheet materials.
- The surfaces of elements that are still in good condition or restored with repair mortar should be roughened sufficiently with grit blasting or similar. With degraded substrates, the whole damaged layer should be removed by scarifying, hydro-demolition or similar and then structural restoration carried out with a suitable repair mortar eg., **EMACO S88C** or **CONCRECIVE 1446**.
- Angle grind, grit blast, or needle gun repair surfaces, to remove smooth, cement paste rich surface (laitance) and ensure aggregate is exposed and the substrate surface has a sufficient profile.
- Remove oils, grease, dust or any other loose material from the surface that may impair adhesion.
- Ensure either a maximum substrate moisture content of 4% or maximum substrate relative humidity of 70% as per AS 1884 – 1995.
- Ensure substrate temperature is at least 3°C above dewpoint temperature.
- Ensure surfaces are within allowable levelness and flatness tolerances.
- Mechanically pre-mix component A before adding component B, using a slow speed drill and mixing paddle.
- When component B has been added, mix slowly to minimise air inclusions, for approximately two minutes until a homogeneous mix has been obtained.
- **MBRACE Primer** may be applied by brush or by roller. (As a guide, surfaces restored with mortars should be cured for a minimum 7 days, prior to primer application).

MBRACE® PRIMER

- Apply subsequent layers of **MBRACE Saturant** or **MBRACE Laminate Adhesive** while the primer is still tacky.
- Clean up excess primer with **Thinner No 1** prior to hardening.

PRECAUTIONS

Only mix sufficient material that may be applied within its workability time.

The climatic and operating conditions of the site and the complexity of the area to be treated should give an indication as to the quantities of product to be mixed.

Excessive vibration and oscillation of the structural component should be avoided during application of the FRP materials and the curing phase of the epoxy resins.

If the **MBRACE Primer** is likely to dry prior to subsequent applications of **MBRACE Saturant** or **MBRACE Laminate Adhesive**, broadcast clean kiln dry sand onto the surface of the still wet primer to ensure a keyed surface. Remove excess sand prior to subsequent material application.

Fire protection requirements must be complied with, as epoxy adhesives generally have limited fire resistance.

SAFETY

READ ALL SAFETY DIRECTIONS AND WARNINGS AND REFER TO MATERIAL SAFETY DATA SHEETS FOR HANDLING PROCEDURES.

Store in a cool, dry area 10 to 32°C away from direct sunlight, flame or other hazards. Do not bend FRP fibre materials or laminates as they may break and become unusable. MBRACE FRP systems contain carbon, aramid and glass fibres. During application of these materials, wear appropriate work clothing to minimise contact.

In particular:

- Always wear gloves, goggles and suitable work clothes during mixing of epoxy resins and working with fibre materials, in order to avoid contact with the skin and eyes.
- In the event of accidental contact, thoroughly wash the affected parts with water and soap or an appropriate detergent.
- Do not add solvents or thinners to the epoxy resins.
- Do not inhale vapours, sprays or fibre dust. A continual change of air should be ensured for application in a closed environment.
- Under no circumstances drink, eat or smoke during use.
- Comply with safety regulations on the use of products that are inflammable or contain solvents.
- Use caution when handling flammable liquids and eliminate all sources of ignition from work area.

For applications to substrate surfaces, extreme climatic conditions or use other than those indicated in the product sheet, please contact your local BASF MBRACE representative or our Technical Department for further information.

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF **Material Safety Data Sheet (MSDS)** from our office or our website.

AMBracePrimer/5/1011

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF**, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd

A.B.N. 62008437867

Head Office: 11 Stanton Road Seven Hills, NSW 2147

Ph. (02) 8811 4200

Newcastle (02) 4961 3819

Canberra (02) 6280 6010

Brisbane (07) 3633 9900

Townsville (07) 4774 7344

Melbourne (03) 9549 0300

Adelaide (08) 8139 7500

Perth (08) 9366 2600

Darwin (08) 8984 3269

Kalgoorlie 0417 772 355

BASF New Zealand Ltd

BASF WEB SITES

Head Office: 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233

www.basf-cc.com.au

www.basf-cc.co.nz

www.meyco.basf.com